

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date  
24 June 2004 (24.06.2004)

PCT

(10) International Publication Number  
WO 2004/053833 A1

(51) International Patent Classification<sup>7</sup>: G10K 11/168 (74) Agent: SEIFERT, Hans-Ulrich; Felber, Seifert & Partner, Dufourstrasse 116/ P.O. Box 380, CH-8034 Zürich (CH).

(21) International Application Number:

PCT/EP2003/013870

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(30) Priority Data:

02027437.9 9 December 2002 (09.12.2002) EP

(84) Designated States (regional): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).


(71) Applicant (for all designated States except US): RIETER TECHNOLOGIES AG [CH/CH]; Schlossalstrasse 43, CH-8406 Winterthur (CH).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ULTRALIGHT TRIM COMPOSITE



WO 2004/053833 A1

(57) Abstract: An ultra light, noise reducing composite (1) comprises an acoustically transparent, light weight film (6) between an underlay layer (5) and an air flow resistance layer (4). This composite allows to easily tune the acoustic properties by balancing the absorption and sound transmission behaviour of the composite (1). This air flow resistance layer (4) has an air flow resistance of between 500N s/m<sup>3</sup> and 10'000Ns/m<sup>3</sup> and an area mass between 200 g/m<sup>2</sup> and 3'000 g/m<sup>2</sup>. The underlay layer (5) has a stiffness value in the range between 100 Pa and 100'000 Pa. The light weight film (6) may consist of a synthetic foil and preferably has a thickness of 0.01 mm.